



Europäisches Patentamt
European Patent Office
Office européen des brevets



(11) Publication number:

0 356 982 B1

(12)

EUROPEAN PATENT SPECIFICATION

- (48) Date of publication of patent specification: **23.12.92** (51) Int. Cl.⁵: **B41M 5/38**
(21) Application number: **89115896.6**
(22) Date of filing: **29.08.89**

(54) **Thermally-transferable fluorescent oxazoles.**

(30) Priority: **31.08.88 US 238655**

(43) Date of publication of application:
07.03.90 Bulletin 90/10

(45) Publication of the grant of the patent:
23.12.92 Bulletin 92/52

(84) Designated Contracting States:
BE CH DE FR GB IT LI NL

(56) References cited:
EP-A- 0 138 483
US-A- 4 627 997

DERWENT JAPANESE PATENTS REPORT, Derwent Publications, Section Printing, Coating and Photographic Chemistry, Vol. 79, No. 46, (E13-G5), page 2; JP-A-49 17 744

PATENT ABSTRACTS OF JAPAN vol. 12, no. 411 (P-779)(3258) 31 October 1988; JP-A-63 147166

(73) Proprietor: **EASTMAN KODAK COMPANY**
343 State Street
Rochester, New York 14650-2201(US)

(72) Inventor: **Henzel, Richard Paul Eastman Kodak Company**
Patent Department 343 State Street
Rochester New York 14650(US)

(74) Representative: **Brandes, Jürgen, Dr. rer. nat. et al**
Wuesthoff & Wuesthoff, Patent- und Rechtsanwälte, Schweigerstrasse 2
W-8000 München 90(DE)

Note: Within nine months from the publication of the mention of the grant of the European patent, any person may give notice to the European Patent Office of opposition to the European patent granted. Notice of opposition shall be filed in a written reasoned statement. It shall not be deemed to have been filed until the opposition fee has been paid (Art. 99(1) European patent convention).

Description

This invention relates to fluorescent donor elements used in thermal transfer.


In recent years, thermal transfer systems have been developed to obtain prints from pictures which have been generated electronically from a color video camera. According to one way of obtaining such prints, an electronic picture is first subjected to color separation by color filters. The respective color-separated images are then converted into electrical signals. These signals are then operated on to produce cyan, magenta and yellow electrical signals. These signals are then transmitted to a thermal printer. To obtain the print, a cyan, magenta or yellow dye-donor element is placed face-to-face with a dye-receiving element. The two are then inserted between a thermal printing head and a platen roller. A line-type thermal printing head is used to apply heat from the back of the dye-donor sheet. The thermal printing head has many heating elements and is heated up sequentially in response to the cyan, magenta and yellow signals. The process is then repeated for the other two colors. A color hard copy is thus obtained which corresponds to the original picture viewed on a screen. Further details of this process and an apparatus for carrying it out are contained in U.S. Patent No. 4,621,271.

The system described above has been used to obtain visible dye images. However, for security purposes, to inhibit forgeries or duplication, or to encode confidential information, it would be advantageous to create non-visual ultraviolet absorbing images that fluoresce with visible emission when illuminated with ultraviolet light.

U.S. Patent 4,627,997 discloses a fluorescent thermal transfer recording medium comprising a thermally-meltable, wax ink layer. In that system, the fluorescent material is transferred along with the wax material when it is melted. Wax transfer systems, however, are incapable of providing a continuous tone. Further, the fluorescent materials of that reference are incapable of diffusing by themselves in the absence of the wax matrix. It is an object of this invention to provide fluorescent materials useful in a continuous tone system which have sufficient vapor pressure to transfer or diffuse by themselves from a donor element to a dye-receiver.



JP-A-49/17744 discloses a heat-sensitive sheet comprising a UV-absorbing dye including oxazole compounds. However, the specific oxazole compounds of the invention are not disclosed.

In accordance with this invention, a donor element for thermal transfer is provided comprising a support having on one side thereof a fluorescent oxazole compound dispersed in a polymeric binder, and on the other side thereof a slipping layer comprising a lubricant, the oxazole compound having the formula:






wherein:




J represents an ethylenic linking group, such as:
 $\{CH=CH\}_n$, where n is 1 to 3,




each J^1 independently represents a monovalent bond or J; and each X and Y independently represents hydrogen; a substituted or unsubstituted alkyl, alkylene or acyl group having from 1 to 10 carbon atoms, such as $-CH_3$,




$-\text{COCH}_3$, or $-\text{CF}_3$; a substituted or unsubstituted aryl group having from 6 to 10 carbon atoms such as $-\text{C}_6\text{H}_5$, $-\text{C}_6\text{H}_5(\text{p}-\text{OCH}_3)$, $-\text{C}_6\text{H}_4(\text{o}-\text{CO}_2\text{CH}_3)$, or $-\text{C}_6\text{H}_4(\text{p}-\text{Cl})$; or the atoms, such as $-\text{NH}$, $-\text{CO}_2$, $-\text{S}$, $-\text{CH}_2$, or $-\text{CH}=\text{CH}$, necessary to complete a 5- or 6-membered carbocyclic or heterocyclic ring, such as



In a preferred embodiment of the invention, the compound employed in the invention has the formula




wherein:
J represents



and each X and Y represents the atoms necessary to complete a 6-membered carbocyclic ring.

In another preferred embodiment of the invention, the compound has the formula




wherein:
J represents



and each X and Y represents phenyl.

In still yet another preferred embodiment, the compound has the formula:




wherein:

each J¹ represents a monovalent bond; and X represents hydrogen.

Compounds included within the scope of the invention include the following:




This material is available commercially as Uvitex OB® from Ciba-Geigy.










This material is available commercially from Kodak Laboratory and Research Chemicals.




This material is available commercially from Kodak Laboratory and Research Chemicals.



Cmpd.	R^1	R^2	J
4	-Cl	$-C_6H_5$	
5	-H	$-C_6H_5$	
6	$-C_6H_5$	-H	
7	-H	$-C_6H_5$	
8	-H	 $-C_6H_5$	
9	-H	$-C_6H_5$	

10


5



10

11


15



20

12


25



30


13

35



40

14



45

50

55

5

10

15

20

25

30


35

40

45

50

55



Compd.	R^3		R^4	R^5
20	-H		$-\text{CH}=\text{CH}-\text{C}_6\text{H}_5$	
21	-H		$-\text{CH}=\text{CH}-\text{CO}_2\text{CH}_3$	
22	$-\text{C}_6\text{H}_5$		$-\text{C}_6\text{H}_5$	$-\text{C}_6\text{H}_5$
23	-H		$-\text{C}_6\text{H}_5$	
24				

5

10

15


20

25

30

35




40



45 A visible dye can also be used in a separate area of the donor element of the invention provided it is transferable to the dye-receiving layer by the action of heat. Especially good results have been obtained with sublimable dyes such as

50

55



30 or any of the dyes disclosed in U.S. Patent 4,541,830. The above dyes may be employed singly or in combination to obtain a monochrome. The dyes may be used at a coverage of from 0.05 to 1 g/m² and are preferably hydrophobic.

35 The fluorescent material in the donor element of the invention is dispersed in a polymeric binder such as a cellulose derivative, e.g., cellulose acetate hydrogen phthalate, cellulose acetate, cellulose acetate propionate, cellulose acetate butyrate, cellulose triacetate; a polycarbonate; poly(styrene-co-acrylonitrile), a poly(sulfone) or a poly(phenylene oxide). The binder may be used at a coverage of from 0.1 to 5 g/m².

The fluorescent material layer of the donor element may be coated on the support or printed thereon by a printing technique such as a gravure process.

40 Any material can be used as the support for the donor element of the invention provided it is dimensionally stable and can withstand the heat of the thermal printing heads. Such materials include polyesters such as poly(ethylene terephthalate); polyamides; polycarbonates; glassine paper; condenser paper; cellulose esters; fluorine polymers; polyethers; polyacetals; polyolefins; and polyimides. The support generally has a thickness of from 2 to 30 μm. It may also be coated with a subbing layer, if desired.

45 The reverse side of the donor element is coated with a slipping layer to prevent the printing head from sticking to the donor element. Such a slipping layer would comprise a lubricating material such as a surface active agent, a liquid lubricant, a solid lubricant or mixtures thereof, with or without a polymeric binder. Preferred lubricating materials include those materials disclosed in U. S. Patents 4,717,711, 4,737,485, 4,738,950, and 4,717,712. Suitable polymeric binders for the slipping layer include poly(vinyl alcohol-co-butyril), poly(vinyl alcohol-co-acetal), poly(styrene), poly(vinyl acetate), cellulose acetate butyrate, cellulose acetate propionate, cellulose acetate or ethyl cellulose.

50 The amount of the lubricating material to be used in the slipping layer depends largely on the type of lubricating material, but is generally in the range of .001 to 2 g/m². If a polymeric binder is employed, the lubricating material is present in the range of 0.1 to 50 weight %, preferably 0.5 to 40, of the polymeric binder employed.

55 The receiving element that is used with the donor element of the invention usually comprises a support having thereon an image-receiving layer. The support may be a transparent film such as a poly(ether sulfone), a polyimide, a cellulose ester such as cellulose acetate, a poly(vinyl alcohol-co-acetal) or a poly-

(ethylene terephthalate). The support for the receiving element may also be reflective such as baryta-coated paper, polyethylene-coated paper, white polyester (polyester with white pigment incorporated therein), an ivory paper, a condenser paper or a synthetic paper such as duPont Tyvek®.

The image-receiving layer may comprise, for example, a polycarbonate, a polyurethane, a polyester, polyvinyl chloride, poly(styrene-co-acrylonitrile), poly(caprolactone) or mixtures thereof. The image-receiving layer may be present in any amount which is effective for the intended purpose. In general, good results have been obtained at a concentration of from 1 to 5 g/m².

As noted above, the donor elements of the invention are used to form a transfer image. Such a process comprises imagewise-heating a donor element as described above and transferring a fluorescent material image to a receiving element to form the transfer image.

The donor element of the invention may be used in sheet form or in a continuous roll or ribbon. If a continuous roll or ribbon is employed, it may have only the fluorescent material thereon as described above or may have alternating areas of different dyes, such as sublimable magenta and/or yellow and/or cyan and/or black or other dyes. Such dyes are disclosed in U. S. Patents 4,541,830, 4,698,651, 4,695,287, 4,701,439, 4,757,046, 4,743,582, and 4,753,922. Thus, one-, two-, three- or four-color elements (or higher numbers also) are included within the scope of the invention.

In a preferred embodiment of the invention, the donor element comprises a poly(ethylene terephthalate) support coated with sequential repeating areas of magenta, yellow, and cyan dye and the fluorescent material as described above, and the above process steps are sequentially performed for each color to obtain a three-color dye transfer image containing a fluorescent image.

A thermal transfer assemblage of the invention comprises

- a) a donor element as described above, and
- b) a receiving element as described above, the receiving element being in a superposed relationship with the donor element so that the fluorescent material layer of the donor element is in contact with the image-receiving layer of the receiving element.

The following example is provided to illustrate the invention.

Example

A donor element was prepared by coating the following layers in the order recited on a 6 µm poly-(ethylene terephthalate) support:

- 1) a subbing layer of duPont Tyzor TBT® titanium tetra-n-butoxide (0.12 g/m²) from 1-butanol; and
- 2) a layer containing the fluorescent material as identified above or control fluorescent material identified below (0.16 g/m²) in a cellulose acetate propionate (2.5% acetyl and 45% propionyl) binder (0.44 g/m²) coated from a cyclopentanone, toluene and methanol solvent mixture.


On the back side of the element was coated:

- 1) a subbing layer of duPont Tyzor TBT® titanium tetra-n-butoxide (0.12 g/m²) from 1-butanol; and
- 2) a slipping layer of Emralon 329® polytetrafluoroethylene dry film lubricant (Acheson Colloids) (0.54 g/m²) coated from a n-propyl acetate, toluene, 2-propanol and 1-butanol solvent mixture.

Control Materials


The following materials are available commercially from Kodak Laboratory Products and Chemicals Division:

Control 1




Fluorescein

Control 2



Rhodamine B

Control 3



DANS Acid

A receiving element was prepared by coating a solution of Makrolon 5705® (Bayer A.G. Corporation) polycarbonate resin (2.9 g/m²) and FC-431® surfactant (3M Corporation) (0.16 g/m²) in a methylene chloride and trichloroethylene solvent mixture on a transparent 175 μm polyethylene terephthalate support.

The fluorescent material layer side of the donor element strip approximately 3 cm x 15 cm in area was placed in contact with the image-receiving layer of the receiver element of the same area. The assemblage was fastened in the jaws of a stepper motor driven pulling device. The assemblage was laid on top of a 14 mm diameter rubber roller and a TDK Thermal Read L-133 (No. 6-2R16-1) and was pressed with a spring at a force of 3.6 kg against the donor element side of the assemblage pushing it against the rubber roller.


The imaging electronics were activated causing the pulling device to draw the assemblage between the printing head and roller at 3.1 mm/sec. Coincidentally, the resistive elements in the thermal print head were pulsed at a per pixel pulse width of 8 msec to generate a graduated density image. The voltage supplied to the print head was approximately 22 v representing approximately 1.6 watts/dot (13 mjoules/dot).

The receiving element was separated from the donor element and the relative emission of the transferred image area was evaluated with a spectrofluorimeter using a fixed intensity 360 nm excitation beam and measuring the relative area under the emission spectrum from 375 to 700 nm. The following results were obtained:

Table

	<u>Compound</u>	<u>Relative Emission*</u>	<u>Visual Color</u>
5	Comparison*	100	Blue
	None	5	Not visible
	Control 1	<1	Not visible
	Control 2	<1	Not visible
10	Control 3	<1	Not visible
	1	91	White
	2	73	Pale Yellow
15	3	11	Purple

* Compared to the following compound, normalized to 100:




This compound is the subject of EP-A-356981, of Byers and Chapman, filed of even date herewith and entitled "Thermally-Transferable Fluorescent 7-Aminocoumarins."

The above results show that the compounds of the invention have much more fluorescence than the control compounds of the prior art.

Claims

1. A donor element for thermal transfer comprising a support having on one side thereof a fluorescent oxazole compound dispersed in a polymeric binder, and on the other side thereof a slipping layer comprising a lubricant, said compound having the formula:




wherein:


J represents an ethylenic linking group; each J¹ independently represents a monovalent bond or J;

and each X and Y independently represents hydrogen; a substituted or unsubstituted alkyl, alkylene or acyl group having from 1 to 10 carbon atoms; a substituted or unsubstituted aryl group having from 6 to 10 carbon atoms; or the atoms necessary to complete a 5- or 6-membered carbocyclic or heterocyclic ring.

2. The element of Claim 1 characterized in that said compound has the formula




wherein:
J represents




and each X and Y represents the atoms necessary to complete a 6-membered carbocyclic ring.

3. The element of Claim 1 characterized in that said compound has the formula




wherein:
J represents



and each X and Y represents phenyl.


4. The element of Claim 1 characterized in that said compound has the formula:



wherein:
each J¹ represents a monovalent bond; and X represents hydrogen.

5. The element of Claim 1 characterized in that said donor element comprises sequential repeating areas of magenta, yellow and cyan dye, and said fluorescent compound.

6. A process of forming a transfer image comprising imagewise-heating a donor element comprising a support having on one side thereof a layer comprising a material dispersed in a polymeric binder, and on the other side thereof a slipping layer comprising a lubricant, and transferring an image to a receiving element to form said transfer image, characterized in that said material is a fluorescent oxazole compound having the formula:



wherein:


J represents an ethylenic linking group; each J¹ independently represents a monovalent bond or J;
and

each X and Y independently represents hydrogen; a substituted or unsubstituted alkyl, alkylene or acyl group having from 1 to 10 carbon atoms; a substituted or unsubstituted aryl group having from 6 to 10 carbon atoms; or the atoms necessary to complete a 5- or 6-membered carbocyclic or heterocyclic ring.

7. A thermal transfer assemblage comprising:

a) a donor element comprising a support having on one side thereof a layer comprising a material dispersed in a polymeric binder, and on the other side thereof a slipping layer comprising a lubricant, and

b) a receiving element comprising a support having thereon an image-receiving layer, said receiving element being in a superposed relationship with said donor element so that said material layer is in contact with said image-receiving layer, characterized in that said material is a fluorescent oxazole compound having the formula:



wherein:


J represents an ethylenic linking group;

each J¹ independently represents a monovalent bond or J; and

each X and Y independently represents hydrogen; a substituted or unsubstituted alkyl, alkylene or acyl group having from 1 to 10 carbon atoms; a substituted or unsubstituted aryl group having from 6 to 10 carbon atoms; or the atoms necessary to complete a 5- or 6-membered carbocyclic or heterocyclic ring.

Patentansprüche

1. Donor-Element für die thermische Übertragung mit einem Träger, auf dessen einer Seite sich eine fluoreszierende Oxazol-Verbindung, dispergiert in einem polymeren Bindemittel, befindet, und auf dessen anderer Seite eine Gleitschicht mit einem Gleitmittel angeordnet ist, wobei die Verbindung der folgenden Formel entspricht:



worin bedeuten:


J eine ethylenische Bindegruppe;

J¹ jeweils unabhängig voneinander eine monovalente Bindung oder gleich J; und

X und Y jeweils unabhängig voneinander Wasserstoff, eine substituierte oder unsubstituierte Alkyl-, Alkylen- oder Acylgruppe mit 1 bis 10 Kohlenstoffatomen; eine substituierte oder unsubstituierte


Arylgruppe mit 6 bis 10 Kohlenstoffatomen; oder die Atome, die zur Vervollständigung eines 5- oder 6-gliedrigen carbocyclischen oder heterocyclischen Ringes erforderlich sind.

2. Element nach Anspruch 1, dadurch gekennzeichnet, daß die Verbindung der folgenden Formel entspricht:




worin :

J für




steht und X und Y jeweils die Atome darstellen, die zur Vervollständigung eines 6-gliedrigen carbocyclischen Ringes erforderlich sind.

3. Element nach Anspruch 1, dadurch gekennzeichnet, daß die Verbindung der folgenden Formel entspricht:




worin:

J darstellt



und X und Y jeweils für Phenyl stehen.


4. Element nach Anspruch 1, dadurch gekennzeichnet, daß die Verbindung der folgenden Formel entspricht: worin:



J¹ jeweils für eine monovalente Bindung steht und X gleich Wasserstoff ist.

5. Element nach Anspruch 1, dadurch gekennzeichnet, daß das Donor-Element aufeinanderfolgende, wiederkehrende Bereiche von purpurrotem, gelbem und blaugrünem Farbstoff sowie der fluoreszierenden Verbindung aufweist.

6. Verfahren zur Herstellung eines Übertragungsbildes, bei dem ein Donor-Element mit einem Träger, auf dessen einer Seite sich eine Schicht mit einem in einem polymeren Bindemittel dispergierten Material befindet und auf dessen anderer Seite eine Gleitschicht mit einem Gleitmittel angeordnet ist, bildweise erhitzt wird und ein Bild auf ein Bildempfangs-Element unter Erzeugung des Übertragungsbildes übertragen wird, dadurch gekennzeichnet, daß das Material eine fluoreszierende Oxazol-Verbindung der folgenden Formel ist:



worin bedeuten:

J eine ethylenische Bindegruppe;


J' jeweils unabhängig voneinander eine monovalente Bindung oder gleich J; und

X und Y jeweils unabhängig voneinander Wasserstoff, eine substituierte oder unsubstituierte Alkyl-, Alkylen- oder Acylgruppe mit 1 bis 10 Kohlenstoffatomen; eine substituierte oder unsubstituierte Arylgruppe mit 6 bis 10 Kohlenstoffatomen; oder die Atome, die zur Vervollständigung eines 5- oder 6-gliedrigen carbocyclischen oder heterocyclischen Ringes erforderlich sind.

7. Satz für die thermische Übertragung mit:

a) einem Donor-Element mit einem Träger, auf dessen einer Seite sich eine Schicht mit einem in einem polymeren Bindemittel dispergierten Material befindet und auf dessen anderer Seite eine Gleitschicht mit einem Gleitmittel angeordnet ist, und

b) einem Empfangselement mit einem Träger, auf dem eine Bildempfangsschicht angeordnet ist, wobei das Empfangselement bezüglich des Donor-Elementes in einer solchen Position angeordnet ist, daß die Materialschicht sich in Kontakt mit der Bildempfangsschicht befindet, dadurch gekennzeichnet, daß das Material eine fluoreszierende Oxazol-Verbindung der Formel ist:



worin bedeuten:


J eine ethylenische Bindegruppe;

J' jeweils unabhängig voneinander eine monovalente Bindung oder gleich J; und

X und Y jeweils unabhängig voneinander Wasserstoff, eine substituierte oder unsubstituierte Alkyl-, Alkylen- oder Acylgruppe mit 1 bis 10 Kohlenstoffatomen; eine substituierte oder unsubstituierte Arylgruppe mit 6 bis 10 Kohlenstoffatomen; oder die Atome, die zur Vervollständigung eines 5- oder 6-gliedrigen carbocyclischen oder heterocyclischen Ringes erforderlich sind.

Revendications

1. Élément donneur de colorant pour transfert de colorant par la chaleur comprenant un support recouvert sur une de ces faces par un composé oxazole fluorescent dispersé dans un liant polymère et sur l'autre face d'une couche favorisant le glissement comprenant un lubrifiant, composé ayant la formule




où


J représente un groupe de liaison éthylénique ; chaque J¹ individuellement représente une liaison monovalente ou J ; et

chaque X et Y individuellement représente un hydrogène ; un groupe alkyle, alkylène ou acyle substitué ou non ayant de 1 à 10 atomes de carbone ; un groupe aryle substitué ou non ayant de 6 à 10 atomes de carbone ; ou les atomes nécessaires pour compléter un noyau carbocyclique ou hétérocyclique à 5 ou 6 chaînons.

2. Élément selon la revendication 1 caractérisé en ce que la composé a la formule




où J représente




et chaque X et Y représente les atomes nécessaires pour compléter un noyau carbocyclique à 6 chaînons.

3. Élément selon la revendication 1 caractérisé en ce que le composé a la formule




où

J représente



et chaque X et Y représente un groupe phényle.


4. Élément selon la revendication 1 caractérisé en ce que le composé a la formule :



où

chaque J¹ représente une liaison monovalente et X représente un hydrogène.

5. Elément selon la revendication 1 caractérisé en ce que l'élément donneur comprend des séquences répétitives de zones de colorants magenta, jaune et cyan et le composé fluorescent.
6. Procédé pour former une image par transfert consistant à chauffer de manière sélective un élément donneur comprenant un support recouvert sur une de ses faces par une couche comprenant une substance dispersée dans un liant polymère et sur l'autre face d'une couche favorisant le glissement comprenant un lubrifiant et à transférer l'image sur un élément récepteur de colorant pour former l'image par transfert, caractérisé en ce que la substance est un composé oxazole fluorescent de formule




où

J représente un groupe de liaison éthylénique ; chaque J' individuellement représente une liaison monovalente ou J ; et

chaque X et Y individuellement représente un hydrogène ; un groupe alkyle, alkylène ou acyle substitué ou non ayant de 1 à 10 atomes de carbone ; un groupe aryle substitué ou non ayant de 6 à 10 atomes de noyau carbocyclique ou hétérocyclique à 5 ou 6 chaînons.

7. Assemblage pour transfert de colorant par la chaleur comprenant :
- a) un élément donneur comprenant un support recouvert sur une de ses faces par une couche comprenant une substance dispersée dans un liant polymère et sur l'autre face par une couche favorisant le glissement comprenant un lubrifiant, et
- b) un élément récepteur comprenant un support recouvert d'une couche réceptrice d'image,
- l'élément récepteur et l'élément donneur étant superposés de telle sorte que la couche comprenant la substance soit en contact avec la couche réceptrice d'image, caractérisé en ce que la substance est un composé polycyclique fluorescent de formule :



où

J représente un groupe de liaison éthylénique ; chaque J' individuellement représente une liaison monovalente ou J ; et

chaque X et Y individuellement représente un hydrogène ; un groupe alkyle, alkylène ou acyle substitué ou non ayant de 1 à 10 atomes de carbone ; un groupe aryle substitué ou non ayant de 6 à 10 atomes de carbone ; ou les atomes nécessaires pour compléter un noyau carbocyclique ou hétérocyclique à 5 ou 6 chaînons.